



Challenger





Challenger

Challenger is a microsuede quality in our Skins Collection. This collection consists only of the best leather looking articles.

Challenger is our ultimate answer to consumers' need for a flawless and easy-to-care-for plain upholstery fabric. Without concessions.

We developed a wonderful new microsuede consisting of two different microfibres. Combined in two layers through a unique process of lamination, which was specially developed for Challenger. Challenger's upper layer is a woven microfibre while the lower layer is knitted. Resulting in a set of productspecifications that leaves furniture with a voluminous and super soft luxury feel. Available in a wide range of contemporary colours to suit every style.

The impact of this high-quality timeless fabric extends beyond its physical appearance. Challenger was developed with comfort in mind. The innovative new finish provides – next to its full grip and a particularly luxurious look – an impeccable appearance in all conditions. Durable for many years of intense and happy living in private homes due to its optimal cleanability, resistance to moisture and breathability.

- Dirt and damp prevention treatment applied.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.

***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside 100%PES
/ microsuede woven

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery




army 14




bronze 116




burgundy 34




cabernet 205




cinnamon 94




coffee 81




darkblue 48




desert 109



forest 162



graphite 66




grey 65




hazel 96

Please note: colours may vary according to your screen settings.




lightgrey 60




liver 10




mustard 06




natural 01




onyx 169




scarlet 141




shell 196



steel 149




taupe 12



teal 198



thyme 206



zinc 167

Please note: colours may vary according to your screen settings.

Challenger - Article passport


Challenger is an unique microsuede consisting of two different microfibres, the faceside layer is woven and the backside is knitted.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	microsuede woven	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%PES	
Composition backside	100%PES	
Bonding	fleece	
Statistic code	60019200	
Dyeing method	piece dyed	
Available colours	24	
Packaging	bubble wrap	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	70.000		min. 8.000	min. 16.000	C
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min.5	C
	middle colours	CTL	grade	4		min. 4	min.5	C
	dark colours	CTL	grade	3-4		min. 4	min.5	C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/A
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 35							
Material weight in grams per linear meter	± 630							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.563	1.137	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	59,3	48,0	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,5	1,5	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	13,7	24,5	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-1,0	-0,8	n/a	n/a	A/A



- Dirt and damp prevention treatment applied.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl